

CS 9943 Tack free accelerator

Chem Seal

*Technical Bulletin
March, 2010*

Product Description

Specifications Lockheed Martin, Flamemaster

CS 9943 Tack free accelerator is designed for application over uncured polysulfide sealants to reduce the Tack Free time by (50 - 80%). CS 9943 significantly reduces the risk of foreign objects and debris (FOD) from adhering to the surface of the uncured sealant. CS 9943 is a one part, low viscosity liquid suitable for application by brush or spray.

Surface Preparation

CS 9943 is applied directly over uncured polysulfide sealants, no special preparation is required. The coating is equally effective for manganese; dichromate lead and epoxy terminated polysulfide sealants.

Color	Amber
Viscosity	Centipoise 1.5
Dry time	<2 hr. 77°F (25°C), 50% rh
Nonvolatile content	5 %
Flash point (TCC)	35°F (1.5°C)
Specific Gravity	0.82

Application

CS 9943 may be applied with the included pump sprayer. Shake well before using. A light mist is optimum.

Shelf Life

CS 9943 has shelf life of is least 6 months when stored at temperatures below 80°F (27°C) in original unopened containers.

Safety

Before using this or any other Chem Seal product, refer to the appropriate MSDS for known hazards and guidance in the safe use of this material. For industrial use only, keep away from children.

Packaging

1 Pint (16 fl/oz), pump spray bottle

All recommendations, statements, and technical data contained herein are based on tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty, either expressed or implied. User shall rely on his own information and tests to determine suitability of the product for the intended use and user assumes all risk and liability resulting from the use of this product. Seller and manufacturer's sole responsibility shall be to replace that portion of the product of this manufacturer, which proves to be defective. Neither seller nor manufacturer shall be liable to buyer or any third person for any injury, loss, or damage directly or indirectly resulting from use of, or inability to use, the product. Recommendations or statements other than those contained in a written agreement signed by an officer of the manufacturer shall not be binding upon the manufacturer or seller.