

CS 3204 R Fast Curing Fuel Tank Sealant

Chem Seal CS 3204 R Class A and B

Technical Bulletin
December, 2008
AMS-S-8802

PRODUCT DESCRIPTION Qualified to AMS-S-8802 Type 2 Class A & B

CS 3204R is a polysulfide based fast curing fuel and temperature resistant (-65° F to 250° F) (-54° C to 121°C) sealant qualified to AMS-S -8802 for use on integral fuel tanks and pressurized cabins. CS 3204R is a two-part polysulfide base compound which cures at room temperature to a flexible, resilient rubber with excellent adhesion to steel, composites, aluminum, magnesium, titanium, and numerous other materials. When mixed, CS 3204R Class B is a thixotropic paste that will not flow or sag on vertical or overhead surfaces application with extrusion gun or spatula, the uncured material is easily tooled

SURFACE PREPARATION

To obtain good adhesion, the surfaces must be free of all traces of contamination. For detailed discussion of proper surface preparation, consult the SAE Aerospace Information Report AIR 4069. This document is available through SAE, 400 Commonwealth Avenue, Warrendale, PA 15096-0001.

MIXING INSTRUCTIONS

Combine Parts A and B using the recommended ratio found on the container label. Stir the curing agent (Part B) component until the contents of the container are uniform. Place the entire B component into the Part A container and continue stirring until a uniform gray color is achieved. There should be no white or black streaks in the properly blended material. Periodically scrape the sides and bottom of the container as well as the mixing tool to assure proper mixing. Users of mechanical mixers should avoid excessive speeds since the heat generated will reduce the application time of the mixed CS 3204R.

For material provided in two component injection kits follow the instructions printed on the packaging

All recommendations, statements, and technical data contained herein are based on tests we believe to be reliable and correct, but accuracy and completeness of said test are not guaranteed and are not to be construed as a warranty, either expressed or implied. User shall rely on his own information and tests to determine suitability of the product for the intended use and user assumes all liability resulting from his use of the product. Sellers and manufacturers sole responsibility shall be to replace that portion of the product of this manufacturer which proves to be defective. Warranty returns accepted only in their original unopened containers no warranty claims accepted for goods repackaged or altered. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss, or damage directly or indirectly resulting from use of, or inability to use, the product. Recommendations or statements other than those contained in a written agreement signed by an officer of the manufacturer shall not be binding upon the manufacturer or seller. Flamemaster does not warranty the performance of fuel tank sealants and coatings subjected to fluids or fuel other than those specified by the applicable specification. It is the responsibility of the user to determine the suitability for use utilizing the information contained in the applicable specification.

CS-3204R Class A & B

Application properties (typical)

Color: Base Compound	off-white
Curing Agent	Black
Mixed	Gray
Mixing Ratio (by weight)	100:10
(by volume)	100:8.2
Non Volatile Content Class B	98%
Non Volatile Content Class A	95%

Viscosity poises

Base Compound Class B	#7 @ 2 RPM	11,000
Base Compound Class A	#6 @ 10 RPM	500 max

<u>Application Class A & B</u>	<u>requirement</u>	<u>observed</u>
Application Class A	2500 max	2300
Extrusion Rate Class B	15 gms min.	30 gms min.

Density	1.65	1.6
Vertical Flow (slump)		< 0.20
Ultimate Hardness	Shore A	60
Air content	4% max	2.4%

Application times and curing times @ 77F 50% RH

application time hours	Typical tack-free time	Typical cure time	Shore A hardness	
A ½	1/2	5	8	35
B ½	1/2	4	6	35
B 2	2	7	15	35

Performance Properties (typical)

Peel strengths (typical)

Paragraph 3.6.20.3 AMSS8802
(10 lbf/ inch – 100% cohesive failure)

<u>Panels</u>	<u>JRF</u>	<u>JRF/SW</u>	<u>% Cohesive</u>
AMS-C-27725	40	45	100%
AMS-C27725 /			
AMS-3100 primer	42	45	100%

All test are in accordance with AMSS8802 using the procedures contained within AS5127 and AS5127/1

CURE

The base conditions for specified application and cure schedules are standard conditions of 77°F and 50% relative humidity. Increase temperature and relative humidity will reduce the work life and speed up the cure while reduced temperatures and relative humidity will extend the work life and extend the cure

STORAGE

The standard storage life of CS-3204R Class B in an injection kit or can kit is at least 9 months when stored at temperatures between 40°F (4.5°C) and 80°F (27°C) in original unopened containers. The storage life of CS-3204R Class B Pre-mixed and frozen is 55 days when stored at temperatures of -40°F (-40°C)

CLEAN UP

For clean up of freshly mixed material use an aromatic solvent. Cured CS 3204R will require a soaking period in epoxy polysulfide stripper.

SAFETY

CS 3204R sealant is a safe material to use when following recommended precautions.. Refer to the applicable Material Safety Data Sheet prior to using this product.

AVAILABILITY

CS-3204R Class B is supplied in two-part Injection kits and Pre-mixed and frozen cartridges. For availability of other packaging contact Flamemaster.

All recommendations, statements, and technical data contained herein are based on tests we believe to be reliable and correct, but accuracy and completeness of said test are not guaranteed and are not to be construed as a warranty, either expressed or implied. User shall rely on his own information and tests to determine suitability of the product for the intended use and user assumes all rand liability resulting from his use of the product. Sellers and manufacturers sole responsibility shall be to replace that portion of the product of this manufacturer which proves to be defective. Warranty returns accepted only in their original unopened containers no warranty claims accepted for goods repackaged or altered. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss, or damage directly or indirectly resulting from use of, or inability to use, the product. Recommendations or statements other than those contained in a written agreement signed by an officer of the manufacturer shall not be binding upon the manufacturer or seller. Flamemaster does not warranty the performance of fuel tank sealants and coatings subjected to fluids or fuel other than those specified by the applicable specification. It is the responsibility of the user to determine the suitability for use utilizing the information contained in the applicable specification.

Performance Properties (typical)

Peel strengths continued
(10 lbf/ inch – 100% cohesive failure)

<u>Panel</u>	<u>JRF</u>	<u>JRF/SW</u>	<u>Cohesive</u>
AS4/3501-6 peel side	38	40	100%
AS4/3501-6 tool side	40	42	100%
AMS 5516 Stainless	42	40	100%
AMS 4911 Titanium	40	37	100%
MIL-PRF-23377 (Baked 200F)	45	45	100%
MIL-PRF-2337 (STD)	42	40	100%
MIL-DTL-81706	35	40	100%

Paragraph 3.6.20.3 AMSS8802
(7 lbf/ inch – 100% cohesive) after 70 days exposure

<u>Panel</u>	<u>JRF</u>	<u>JRF/SW</u>	<u>Cohesive</u>
AMS-C-27725	40		100%

Tensile Strength and Elongation
JRF – AMS2629 Type I

<u>Para.</u>	<u>Required</u>	<u>Result</u>	<u>Conditioning</u>
3.6.17.1	200 psi/200%	299 psi/800%	Std conditions 14 days in JRF - 140F
3.6.17.2	50 psi/200%	128psi/600%	7 days in JRF – 250F in air
3.6.17.3	25 psi/100%	344 psi/ 450%	72 hrs-JRF - 140F+72 hrs- 120F-air+7 days-250F-air
3.6.17.4	200 psi/ 75%	380 psi/ 300%	24 days-250F+7 days-JRF-140F
3.6.17.5	100 psi/150%	216 psi/ 650%	

<u>Properties</u>	<u>Required</u>	<u>Result</u>
<u>Repairability min</u> Itself / AMS3276	10 lbf / 100%	35 lbf / 100%
<u>Thermal rupture</u> No blistering	0.125 max – 250F	0.011 / Pass
<u>Corrosion</u> Under sealant	None	Pass
<u>Chalking max</u> AMS2629 Type II	Slight	Pass

Application and performance properties are typical all tests conducted under controlled conditions. Reference AMSS8802 and AS5127 –AS5127/1 for requirements and procedures.