

PA 2 Primer Activator

Dyna Therm

**Technical Bulletin
June, 2003**

PRODUCT DESCRIPTION meets MMS-K-364

PA-2 is one component of a room temperature curing, low density silicone rubber thermal insulating ablative coating system. PA-2 may be added to mixed and thinned S-885 (Low Density Silicone Ablative) material. PA-2 is used to increase cure time and hardness. The addition of PA-2 will reduce the pot life of the coating material.

Color	Colorless
Specific Gravity	0.8
Percent Solids	20%
Shelf Life	2 Years

MIXING INSTRUCTIONS

Initially add 2 ml of PA-2 per 100 grams of base coating to the mixed and thinned material. If a shore A of 50 is not obtained, remix a batch of material and add 5 ml of PA-2 per 100 grams of base material.

PACKAGING

PA-2 is packaged in gallons

STORAGE LIFE

Shelf life for PA-2 is 2 years when stored below 70°F

SAFETY

PA-2 is a flammable liquid, eliminate all sources of ignition, wear gloves and face shield when transferring this material. For health and safety information, consult the Material Safety Data Sheet provided with this product

All recommendations, statements, and technical data contained herein are based on tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty, either expressed or implied. User shall rely on his own information and tests to determine suitability of the product for the intended use and user assumes all risk and liability resulting from his use of the product. Seller's and manufacturer's sole responsibility shall be to replace that portion of the product of this manufacturer which proves to be defective. Neither seller nor manufacturer shall be liable to buyer or any third person for any injury, loss, or damage directly or indirectly resulting from use of, or inability to use, the product. Recommendations or statements other than those contained in a written agreement signed by an officer of the manufacturer shall not be binding upon the manufacturer or seller.

Dyna Therm Products
Manufactured By The Flamemaster Corporation
11120 Sherman Way Sun Valley, California 91352
Phone: 818 982-1650 *** Fax: 818 765-5603

Supersedes December, 1999 Page 1 of 1